

### AMENDMENTS TO THE CLAIMS

Please amend Claims 1-6 and 8 as set forth below. Please cancel claim 7 without prejudice or disclaimer.

#### LISTING OF CLAIMS

1. (Currently amended) A photochromic polyurethane laminate film comprising:  
a polyurethane film layer having a thickness in the range of about 10  $\mu\text{m}$  to 250  $\mu\text{m}$ ;  
said polyurethane film layer being sandwiched between an inner and outer protective resin layer  
said polyurethane film layer comprising:
  - at least one organic photochromic compound;
  - a stabilizer system having two hindered amine light stabilizers and one phenolic antioxidant and the absence of a UV light absorber;
  - said photochromic compound having a concentration of approximately 0.1% to 6% by weight of said polyurethane film layer;
  - said stabilizer system having a concentration of approximately 1% to 9% by weight of said polyurethane film layer;
  - said stabilizer system having a formulation to provide at least a 40%  $\phi$  improvement in the light fatigue resistance of the photochromic polyurethane film layer over a film layer not having said formulation; and
  - said stabilizer system having a formulation to provide a change of less than 6 units in  $b^*$  of CIELAB at the clear state for said photochromic polyurethane film layer.

2. (Currently amended) A photochromic polyurethane lamine film of Claim 1 wherein said stabilizer system comprises:

(a) 60% to 90%, by weight, two hindered amine light stabilizers being selected from the group consisting of bis(1,2,2,6,6-pentamethyl-4-piperidinyl)-[[3,5-bis(1,1-dimethylethyl)]-[4-hydroxyphenyl]methyl]butyl malonate; Bis(1,2,2,6,6-pentamethyl-4-piperidinyl) sebacate; methyl (1,2,2,6,6-pentamethyl-4-piperidinyl) sebacate; bis(2,2,6,6-tetramethyl-4-piperidinyl)decanedioate; 1-acetyl-4-(3-dodecyl-2,5-dioxo-1-pyrrolidinyl)-2,2,6,6-tetramethyl-piperidine and N-unsubstituted HALS compounds, and N-methylated HALS compounds; and

(b) 10% to 40%, by weight, one phenolic antioxidant being selected from the group consisting of tetrakis-(methylene-3-(3',5'-di-*t*-butyl-4'-hydroxyphenyl) propionate)methane; 1,3,5-trimethyl-2,4,6-tris(3,5-di-*t*-butyl-4'-hydroxybenzyl)benzene; 1,3,5-tris(3,5-di-*t*-butyl-4'-hydroxybenzyl)isocyanurate; 3,5-di-*t*-butyl-4-hydroxyhydrocinnamic triester with 1,3,5-tris(2-hydroxyethyl)s-triazine-2,4,6-(1H,3H,5H)-trione; and 1,3,5-tris(4-*t*-butyl-3-hydroxy-2,6-dimethylbenzyl)s-triazine-2,4,6-(1H, 3H,5H)-trione; and

3. (Currently amended) A photochromic polyurethane lamine film of claim 2 wherein said two hindered amine light stabilizers are bis(1,2,2,6,6-pentamethyl-4-piperidinyl)-[[3,5-bis(1,1-dimethylethyl)]-[4-hydroxyphenyl]methyl]butyl malonate and a Bis(1,2,2,6,6-pentamethyl-4-piperidinyl) sebacate – methyl (1,2,2,6,6-pentamethyl-4-piperidinyl) sebacate blend, and said phenolic antioxidant is tetrakis-(methylene-3-(3',5'-di-*t*-butyl-4'-hydroxyphenyl) propionate)methane.

4. (Currently amended) A photochromic polyurethane lamine film of claim 1 wherein said photochromic compound is a photochromic naphthopyran.

5. (Currently amended) A photochromic polyurethane lamine film of claim 1 wherein said polyurethane is an aliphatic polyurethane.

6. (Currently amended) A photochromic polyurethane laminate film of claim 1 wherein said polyurethane is an aliphatic polyester polyurethane.
7. (Canceled)
8. (Currently amended) A photochromic polyurethane laminate film of claim ~~7~~ 1 wherein the laminate is incorporated into an eyewear lens.